


SCIENTIFIC LABORATORIES, INC.

13635 GENITO ROAD

MIDLOTHIAN, VA 23112

TEL: (804) 763-1200 • FAX: (804) 763-1800

PLM Bulk Asbestos Report

New York Environmental Law &
Justice Project
Attn: Joel Kupferman
315 Broadway
Suite # 200
New York, NY 10007-1121

Date Received 07/29/2002 SciLab Job No. 102071900
Date Examined 07/31/2002 P.O. # FD25-07-27
Page 1 of 1
RE: FD25-07-27

Client No. / HGA	Lab No.	Asbestos Present	Total % Asbestos
150	102071900-01	Yes	3 %

Location: Ladder 25

Description: White/Grey, Heterogeneous, Bulk Material
Asbestos Types: Chrysotile 3. %
Other Material: Fibrous glass 40. %, Non-Asbestos 57. %

100	102071900-02.1	No	NAD
-----	----------------	----	-----

Location: Ladder 25

Description: White/Grey, Heterogeneous, Paper Material
Asbestos Types:
Other Material: Cellulose 100. %

100	102071900-02.2	Yes	2 %
-----	----------------	-----	-----

Location: Ladder 25

Description: White/Grey, Heterogeneous, Debris Material
Asbestos Types: Chrysotile 2. %
Other Material: Fibrous glass 40. %, Non-Asbestos 58. %

Reporting Notes:

Analyzed by: C. Samuel Manooch

Date

07/31/02

*NAD/NSD = no asbestos detected; Detection Limit <1%; NA = not analyzed; NA/PS = not analyzed / positive stop; PLM Bulk Asbestos Analysis by EPA 600/M4-82-020 per 40 CFR 763 (NVLAP Lab #101904-0) and ELAP PLM Analysis Protocol 198.1 for New York samples (NYSDOH ELAP Lab # 10984); CA ELAP Lab # 2508; Note: PLM is not consistently reliable in detecting asbestos in floor coverings and similar non-friable organically bound materials. TEM is currently the only method that can be used to determine if this material can be considered or treated as non-asbestos-containing in New York State (also see EPA Advisory for floor tile, FR 59, 146, 38970, 8/1/94). National Institute of Standards and Technology Accreditation requirements mandate that this report must not be reproduced except in full without the approval of the laboratory. This PLM report relates ONLY to the items tested.